

IN THE CLAIMS

22. (Four Times Amended) A cloth prepreg made by a wet process comprising a woven fabric impregnated with a resin and a binder distributed in a line-like manner on the fabric to maintain yarn flatness,

the fabric comprising a number of crossing points of warp and weft in a range of from 2,000 to 70,000/m², said warp and said weft being substantially free from twist, a width of 3 to 20 mm and a flatness as defined by a ratio of yarn width to yarn thickness of at least 20,

the prepreg having a cover factor of at least 90% and

wherein an amount of the binder used is within about 0.5 to 15 g/m².